

EPDM 6o Compound 559843



ERIKS' 559843 is a specialist grade peroxide cured EPDM compound developed for potable water applications with improved chemical and thermal resistance. The compound is particularly suitable for hot (chloramine treated) drinking water as well as food and beverage applications.

Description

Chemical composition: Terpolymer of ethylene, propylene and diene

Physical form: O-rings, moulded parts

Colour: Black

Temperature resistance: -45°C to +150°C

Application

- Potable water
- Hot water and steam
- Organic and inorganic acids
- Covalent or non polar solvents

Compliances

- DVGW W270
- KIWA-ATA
- UBA Elastomerleitlinie
- WRAS
- FDA 21 CFR 177.2600
- EC1935:2004
- EN681-1 WA-WB-WC-WD
- ADI
- REACH
- RoHS

Please consult our [Chemical Resistance Guide](#) for more information on this compound.



Table 1: Physical properties

Property	Test standard	Value	Unit
Hardness	ISO 48	57±5	IRHD
Elongation at break	ISO 37	450	%
Tensile strength	ISO 37	13.3	MPa
100% Modulus	ISO 37	1.66	MPa
Compression set – 22 hours at 125°C Slab	ISO 815	19	%

Table 2: Ageing properties

Property	Test standard	Value	Unit
Ageing water – 70 hours at 100°C	ISO 1817		
Hardness change		-1	IRHD
Elongation at break change		-1	%
Tensile strength change		-6	%
Volume change		+1.6	%

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or incomplete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.