

## Genuine Viton® 70-compound 514670 - Technical Data Sheet

### 1. Introduction

Original Viton® 514670-compound is based on a 100% Genuine Viton® polymer. Products out of this compound are being made according to strict guidelines of DuPont Performance Elastomers. This guarantees a constant high quality level. All products carry the specific, easy recognizable emblem on their package. In conformity with FDA 177.2600.

### 2. Product Description

Chemical Composition :	Dipolymer of Hexa-Fluoropropylene and Vinylidene Fluoride, plus cure chemicals with 66% Fluorine
Physical form :	O-Rings / Mouldings
Colour :	Black
Odour :	None
Storage stability * :	Excellent

\* : Following ISO 2230 conditions

### 3. Physical Properties

Test Method	Norm	Test Values
Hardness	ISO 48 Method M	70 ± 5 IRHD
Tensile Strength at break	ISO 37	min 16,9 MPa
Elongation at break	ISO 37	min 261%
Specific Weight	ISO 2781	1,82
Compression Set 25% compression - 24h/200°C on slab	ISO 815 ISO 815	max 15%
Heat Ageing 7 days/150°C Hardness Change Volume Change	ISO 188	max -2° max +3%

### 4. Temperature Resistance

- -20° to +200°C
- TR10 (low temp. resistance): -16°C

### 5. Chemical Resistance

Concentrated acids	: excellent
Acetone	: bad
Hydroxides	: excellent
Benzene	: excellent
Crude oil	: excellent
Toluene	: excellent
Fuel C	: excellent
Gasoline	: very good
BTM oil 3	: excellent
Methylene chloride	: very good
MEK	: bad
MTBE	: bad
Water < 100°C	: very good

### 6. Advantages

- Very good compression-set
- Compression-moulded, produced in small quantities
- Migration tested in compliance with FDA 177.2600 class 1 (certificate on request)

### 7. Other Information

- Produced with high purity furnace black N772
- Contains less than 10% high purity furnace black (class 1)
- This compound is ADI (Animal Derived Ingredient Free).

