

NBR 70-compound 32770 - Technical Data Sheet

1. Introduction

NBR 70-compound 32770 is a Buna N compound for gas applications.

2. Product Description

Chemical Composition	: Acrylonitrile / Butadiene Rubber
Physical form	: O-Rings / Mouldings
Colour	: Black
Odour	: None
Storage stability *	: ± 5 years

* : Following ISO 2230 conditions

Test Method	Norm	Test Values
Hardness	ISO 48 Method M	70° ± 5° IRHD
Tensile Strength at break	ISO 37	13,3 MPa
Elongation at break	ISO 37	350%
Air Ageing 24h/100°C	ISO 188	-5%
Compression Set	ISO 815	
40% compression, 72h/23°C		7%
25% compression, 24h/100°C		12%
25% compression, 72h/-5°C		16%
Stress Relaxation		
Stress decrease per timedecade		1,9%
Stress increase after immersion in iso-octaan/toluene (70-30)		5%
Stress decrease after drying		7%
Immersion in iso-octaan/toluene (70-30)	ISO 1817	
Volume Change at 72h/23°C		+26%
Weight Change after drying		-0,1%
Immersion in demineralized water	ISO 1817	
Volume Change at 72h/23°C		+0,6%
Weight Change after drying		-0,2%
Ozone Resistance		
20% elongation at 120h/40°C		No attack

4. Temperature Resistance

- -30° to +120°C

5. Chemical Resistance

Alkali	: very good
Air	: excellent
Alcohol	: very good
Fats	: excellent
Mineral oils	: excellent
Silicone oils	: excellent
Vegetable oils	: excellent
Inorganic acids	: excellent
Ketones	: unsatisfactory
Ethers	: unsatisfactory
Organic acids	: fair
Inorganic acids	: excellent

6. Advantages

- For gas applications

7. Other Information

- In conformity with NEN 7212 Dutch Gastec QA.



This information is, to the best of our knowledge, accurate and reliable to the date indicated. The above mentioned data have been obtained by tests we consider as reliable. We don't assure that the same results can be obtained in other laboratories, using different conditions by the preparation and evaluation of the samples.