



NBR 90 Compound 47702

ERIKS' 47702 is a standard grade nitrile compound with a medium percentage of acrylonitrile. Suitable for high pressure applications.

Description

- Chemical composition: Acrylonitrile-butadiene rubber (nitrile)
- Physical form: O-rings, moulded parts
- Colour: Black
- Temperature resistance: -30°C to +120°C

Application

- General purpose
- Hydrocarbons
- High pressure

Compliances

- ADI
- REACH
- RoHS

Additional information

■ Wide range of O-rings available from stock

Please consult our <u>Chemical Resistance Guide</u> for more information on this compound.







Table 1: Physical properties

Property	Test standard	Value	Unit
Hardness	ISO 48	89±5	IRHD
Elongation at break	ISO 37	150	%
Tensile strength	ISO 37	16	MPa
Compression Set – 24 hours at 100°C Slab	ISO 815	13	%

Table 2:

Property	Test standard	Value	Unit
Heat ageing – 70 hours at 100°C	ISO 188		
Hardness change		+4	IRHD
Elongation at break change		-22	%
Tensile strength change		+5	%
Immersionin ASTM oil nr. 3 – 70 hours at 100°C	ISO 1817		
Hardness change		-5	IRHD
Elongation at break change		-10	%
Tensile strength change		-4	%
Volume change		+4	%

M01120000009-en_14.08.2015

Disclaimer: The content of this document has been composed with the utmost care. However, it is possible that certain information changes over time, becomes inaccurate or incomplete. ERIKS does not guarantee that the information provided on this document is up to date, accurate and complete; the information provided is not intended to be advice. ERIKS shall never be liable for damage resulting from the use of the information provided.